

Chemical Name	Rating*
2 - butanone	A
Acetic acid	A
Acetylene	A
Alkalines	A
Ammonia	A
Amyl chloride	A
Analine	A
Aqua Regia	A
Benzaldehyde or Benzotrile	A
Benzenesulfonic Acid	A
Bromine	A
Calcium Hypochlorite	A
Camphor Oil or Carbon Sulfide	A
Carbon Tetrachloride	A
Chloral Hydrate or Chloroacetic Acid	A
Chlorine or Bleaching Agents	A
Chloroform or Chorosulfonic acid	A
Chromic Acid	A
Concentrated Oxidizing Acids	A
Creosote or Cresol	A
Decalin or Dichlorobenzene	A
Diethyl Ether or Dimethylamine	A
Dimethyl Sulfoxide	A
Ethyl Acetate	A
Ethylene & Propylene Dichloride	A
Ferric Chloride	A
Ferric Nitrate	A
Ferric Sulfate	A
Ferrous Sulfate	A
Fluoboric Acid	A
Fluorinating Agents, Strong	NR
Fluorine > 140°F & Dry Gas > 250°F	NR
Fluosilicic Acid	A
Hydrobromic Acid	A

Chemical Name	Rating
Hydrochloric Acid	A
Hydrocyanic Acid	A
Hydrofluoric Acid	A
Hydrofluosilicic Acid	A
Hydrogen Fluoride, Dry > 250°F	NR
Hydrogen Peroxide	A
Hydrogen Sulfide, Moist	A
Hydroxides	A
Mercury or Silver Salts	A
Methyl Chloride or MEK	A
Molten Alkali Metals	NR
Molten Anhydrous Bases	NR
Nitric Acid	A
Nitro Benzene	A
Oleum	A
P-dioxane or Phenol	A
Partly Halogenated Hydrocarbons	A
Phosphoric Acid	A
Potassium Chlorate	A
Potassium or Sodium Cyanide	A
Potassium Dichromate or Nitrate	A
Potassium Hydroxide	A
Sodium Chlorate	A
Sodium Hydroxide	A
Sodium Nitrate	A
Stannous Chloride	A
Sulfur Dioxide, 5% + H ₂ O	A
Sulfur, Molten	A
Sulfuric acid	A
Tetralin or Trichlorethylene	A
Toluene	A
Trifluoroacetic Acid	A
Xylene	A
Zinc Chloride	A

*Ratings: A = Acceptable

NR = Not Recommended

Revised July, 01

Warranty Information: All information contained herein is believed to be correct but is presented without any guaranty, warranty or representation of any kind, express or implied. Suggestions concerning possible applications of our products are made without representation or warranty that such use is free from patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other such measures may not be required. Changes in temperature, concentration and/or combinations of chemicals may cause different results. Prior to use, it is recommended that the material be tested to determine its compatibility with a specific application.