

Rulon® LR

The following table is a list of typical physical property values for Rulon® LR

Properties	ASTM	Units [Metric]	Value [Metric]
GENERAL			
Specific Gravity	D792	—	2.25
Hardness Shore D	D2240	—	60 to 75
Water Absorption	D570	%	0
MECHANICAL			
Tensile Strength	D4894	psi [MPa]	1,500 [10.3]
Elongation	D4894	%	150
Deformation under load 1500 psi, 24 Hrs., RT	D621	%	3.0
Izod Impact Strength (notched)	D256	FT-lb/in [J/m]	6.0 [320]
THERMAL			
Thermal Conductivity	D2214	BTU in/hr ft ² °F [W/m.K]	2.3 [0.33]
Flammability	D635	In/min [m/s]	Non-flammable
ELECTRICAL			
Dielectric Strength, .080" thick	D149	V/mil [MV/m]	400 [15.7]
Dielectric Strength, .010" thick	D149	V/mil [MV/m]	900 [35.5]
Dielectric Constant	D150	—	2.5
Dissipation Factor	D150	—	.001 – .004
Surface Resistivity	D257	Ohm-Sq	2 x 10 ¹³
Volume Resistivity	D257	Ohm-cm	1 x 10 ¹⁵
RECOMMENDED OPERATING LIMITS			
Maximum Pressure (P)	—	psi [MPa]	1,000 [6.9]
Maximum Velocity (V) no pressure	—	ft/min [m/s]	400 [2]
Maximum PV (P x V)	—	psi x ft/min [MPa x m/s]	10,000 [0.35]
Minimum Mating Surface Hardness			
Rockwell Scale	—	—	Rc35
Brinnell Scale	—	—	327
Tribological			
Friction – static & dynamic	—	—	0.15 – 0.25

Features / Benefits

- Compatible with most hardened steel substrates
- Chemical Inertness
- Long life & reliability in continuous non-lubricated applications

Working Temperature Range

- 400 °F to + 550 °F
[- 240 °C to + 288 °C]

Color

- Maroon

Warranty Information: All information contained herein is believed to be correct but is presented without any guarantee, warranty or representation of any kind, express or implied. Technical data set forth herein is based on tests and measurements conducted in our laboratory under controlled conditions. Suggestions concerning possible applications of our products are made without representation or warranty that such use is free from patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other such measures may not be required.

Saint-Gobain Performance Plastics Corporation

Bristol, RI 02809 USA
Tel: (401) 253-2000
Fax: (401) 253-8211

Saint-Gobain Performance Plastics N.V.

B-2550 Kontich – Belgium
Phone : +32 3 458 28 28
Fax : +32 3 458 26 69

Saint-Gobain KK Performance Plastics

Tokyo 102-0083, Japan
Phone : +81 33 26 30 285
Fax : +81 33 26 30 286

www.plastics.saint-gobain.com

Rulon® is a registered trademark.
© 2006 Saint-Gobain Performance Plastics Corporation
SGPPL.BR.TDS.014.2006

Coefficient of Thermal Expansion		x 10 ⁻⁵ m/m°C		x 10 ⁻⁵ in/in°F	
ASTM D696		Cross Direction	Molded Direction	Cross Direction	Molded Direction
-125 to +77 °F	-87 to +25 °C	7.2	11.7	4.0	6.5
-75 to +77 °F	-59 to +25 °C	8.1	13.3	4.5	7.4
-24 to +77 °F	-31 to +25 °C	9.5	16.5	5.3	9.2
0 to +77 °F	-18 to +25 °C	10.2	18.5	5.7	10.3
+32 to +77 °F	0 to +25 °C	11.8	21.9	6.6	12.2
+48 to +77 °F	+9 to +25 °	10.4	15.3	5.8	8.5
+77 to +150 °F	+ 25 to +66 °C	7.0	9.2	3.9	5.1
+77 to +250 °F	+ 25 to +121 °C	7.7	9.5	4.3	5.3
+77 to +350 °F	+ 25 to +177 °C	9.2	10.6	5.1	5.9
+77 to +450 °F	+ 25 to +232 °C	11.1	12.2	6.2	6.8
+77 to +550 °F	+ 25 to +288 °C	14.7	15.6	8.2	8.7

Cross Direction: Parallel to length of molded or extruded rod or tube.

Molded Direction: Perpendicular to length of molded or extruded rod or tube.

NOTE: The data listed here falls within the normal range of properties but should not be used to establish specification limits nor used alone as the basis of design. Saint-Gobain Performance Plastics assumes no obligation or liability for any advice furnished by it or for results obtained with respect to the products.