

# Rulon® 1045

The following table is a list of typical physical property values for Rulon® 1045

Properties	ASTM	Units [Metric]	Value [Metric]
<b>GENERAL</b>			
Specific Gravity	D792	—	2.11
Hardness Shore D (nominal)	D676	—	55
<b>MECHANICAL</b>			
Tensile Strength	D4894	psi [MPa]	3,900 [26.9]
Elongation	D4894	%	450
<b>THERMAL</b>			
Flammability	D635	In/min [m/s]	Non-flammable
<b>RECOMMENDED OPERATING LIMITS</b>			
Maximum Pressure (P)	—	psi [MPa]	1,000 [6.9]
Maximum Velocity (V) no pressure	—	ft/min [m/s]	400 [2]
Maximum PV (P x V)	—	psi x ft/min [MPa x m/s]	10,000 [0.35]
<b>Minimum Mating Surface Hardness</b>			
Rockwell Scale	—	—	Rb25
<b>Tribological</b>			
Friction – static & dynamic	—	—	0.10 – 0.20

Coefficient of Thermal Expansion		x 10 <sup>-5</sup> m/m°C		x 10 <sup>-5</sup> in/in°F	
TMA		Cross Direction	Molded Direction	Cross Direction	Molded Direction
78 to 200 °F	26 to 93 °C	9.3	12.2	5.2	6.8

Cross Direction: Parallel to length of molded or extruded rod or tube.

Molded Direction: Perpendicular to length of molded or extruded rod or tube.

## Features / Benefits

- Excellent ability to elongate in flip seal application
- Increased sealing efficiency
- Resistant to many harsh chemicals
- Compatible with most commercial lubricants

## Working Temperature Range

- - 400 °F to + 550 °F  
[- 240 °C to + 288 °C]

## Color

- Dull Gold

**Warranty Information:** All information contained herein is believed to be correct but is presented without any guarantee, warranty or representation of any kind, express or implied. Technical data set forth herein is based on tests and measurements conducted in our laboratory under controlled conditions. Suggestions concerning possible applications of our products are made without representation or warranty that such use is free from patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other such measures may not be required.

### Saint-Gobain Performance Plastics Corporation

Bristol, RI 02809 USA  
Tel: (401) 253-2000  
Fax: (401) 253-8211

### Saint-Gobain Performance Plastics N.V.

B-2550 Kontich – Belgium  
Phone : +32 3 458 28 28  
Fax : +32 3 458 26 69

### Saint-Gobain KK Performance Plastics

Tokyo 102-0083, Japan  
Phone : +81 33 26 30 285  
Fax : +81 33 26 30 286

[www.plastics.saint-gobain.com](http://www.plastics.saint-gobain.com)

Rulon® is a registered trademark.  
© 2006 Saint-Gobain Performance Plastics Corporation  
SGPPL.BR.TDS.039.2006

**NOTE:** The data listed here falls within the normal range of properties but should not be used to establish specification limits nor used alone as the basis of design. Saint-Gobain Performance Plastics assumes no obligation or liability for any advice furnished by it or for results obtained with respect to the products.