

Rulon® AR CHEMICAL RESISTANCE

CHEMICAL	RATING
2 - butanone	A
Acetic acid	A
Acetylene	A
Alkalines	A
Ammonia	A
Amyl chloride	A
Analine	A
Aqua Regia	A
Benzaldehyde or Benzonitrile	A
Benzenesulfonic Acid	A
Bromine	A
Calcium Hypochlorite	A
Camphor Oil or Carbon Sulfide	A
Carbon Tetrachloride	A
Chloral Hydrate or Chloroacetic Acid	A
Chlorine or Bleaching Agents	A
Chloroform or Chorosulfonic acid	A
Chromic Acid	A
Concentrated Oxidizing Acids	A
Creosote or Cresol	A
Decalin or Dichlorobenzene	A
Diethyl Ether or Dimethylamine	A
Dimethyl Sulfoxide	A
Ethyl Acetate	A
Ethylene & Propylene Dichloride	A
Ferric Chloride	A
Ferric Nitrate	A
Ferric Sulfate	A
Ferrous Sulfate	A
Fluoboric Acid	NR
Fluorinating Agents, Strong	NR
Fluorine > 140°F & Dry Gas > 250°F	NR
Fluosilicic Acid	NR
Hydrobromic Acid	A

CHEMICAL	RATING
Hydrochloric Acid	A
Hydrocyanic Acid	A
Hydrofluoric Acid	NR
Hydrofluosilicic Acid	NR
Hydrogen Fluoride, Dry > 250°F	NR
Hydrogen Peroxide	A
Hydrogen Sulfide, Moist	A
Hydroxides	NR
Mercury or Silver Salts	A
Methyl Chloride or MEK	A
Molten Alkali Metals	NR
Molten Anhydrous Bases	NR
Nitric Acid	A
Nitro Benzene	A
Oleum	A
P-dioxane or Phenol	A
Partly Halogenated Hydrocarbons	A
Phosphoric Acid	A
Potassium Chlorate	A
Potassium or Sodium Cyanide	A
Potassium Dichromate or Nitrate	A
Potassium Hydroxide	NR
Sodium Chlorate	A
Sodium Hydroxide	A
Sodium Nitrate	A
Stannous Chloride	A
Sulfur Dioxide, 5% + H ₂ O	A
Sulfur, Molten	A
Sulfuric acid	A
Tetralin or Trichlorethylene	A
Toluene	A
Trifluoroacetic Acid	A
Xylene	A
Zinc Chloride	A



A = ACCEPTABLE

NR = NOT RECOMMENDED

Warranty Information: All information contained herein is believed to be correct but is presented without any guarantee, warranty or representation of any kind, express or implied. Technical data set forth herein is based on tests and measurements conducted in our laboratory under controlled conditions. Suggestions concerning possible applications of our products are made without representation or warranty that such use is free from patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other such measures may not be required.

Saint-Gobain Performance Plastics Corporation

Bristol, RI 02809 USA
Tel: (401) 253-2000
Fax: (401) 253-8211

Saint-Gobain Performance Plastics N.V.

B-2550 Kontich – Belgium
Phone : +32 3 458 28 28
Fax : +32 3 458 26 69

Saint-Gobain KK Performance Plastics

Tokyo 102-0083, Japan
Phone : +81 33 26 30 285
Fax : +81 33 26 30 286

www.plastics.saint-gobain.com

Rulon® is a registered trademark.
© 2006 Saint-Gobain Performance Plastics Corporation
SGPPL.BR.TDS.016.2006